

**This page is mainly introduced the 17-7PH chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of 17-7PH, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.**

## Data Table for Grades Stainless Steels 17-7PH

| 17-7PH Standard Number: |                      |  |
|-------------------------|----------------------|--|
| ITEM                    | Standard Number      | Descriptions   |
| 1                       | SAE AMS 5528H (2007) | Steel, Corrosion-Resistant, Sheet, Strip, and Plate 17Cr - 7.1Ni - 1.1Al Solution Heat Treated, Precipitation Hardenable   |
| 2                       | SAE AMS 5529J (2012) | Steel, Corrosion Resistant, Sheet and Strip 17Cr - 7.1Ni - 1.1Al Solution Heat Treated and Cold Rolled, Precipitation Hardenable 0.0015 to 0.050 Inch (0.038 to 1.27 mm) Nominal Thickness |
| 3                       | SAE AMS 5568G (2011) | Steel, Corrosion and Heat Resistant, Welded Tubing 17Cr - 7.1Ni - 1.1Al Solution Heat Treated, Precipitation-Hardenable  |
| 4                       | SAE AMS 5644D (1964) | Steel Bars and Forgings, Corrosion Heat Resistant 17Cr - 7Ni - 1Al   |
| 5                       | SAE AMS 5678F (2007) | Steel, Corrosion Resistant, Wire 17Cr - 7.1Ni - 1.1Al Cold Drawn, Precipitation-Hardenable   |
| 6                       | SAE J 217 (1994)     | Stainless steel 17-7 PH spring wire and springs  |
| 7                       | SAE J 467 (1968)     | Special Purpose Alloys ("Superalloys")   |

| 17-7PH Chemical composition(mass fraction)(wt.%) |         |         |
|--|---------|---------|
| Chemical   | Min.(%) | Max.(%) |
| C  |         | 0.09    |
| Si   |         | 1.00    |
| Mn   |         | 1.00    |
| P  |         | 0.040   |
| S  |         | 0.040   |
| Ni   | 6.50    | 7.75    |
| Cr   | 16.00   | 18.00   |
| Al   | 0.75    | 1.50    |

| 17-7PH Physical Properties |         |                          |
|----------------------------|---------|--------------------------|
| Tensile strength           | 115-234 | $\sigma_b$ /MPa          |
| Yield Strength             | 23      | $\sigma_{0.2} \geq$ /MPa |
| Elongation                 | 65      | $\delta_5 \geq$ (%)      |
| $\psi$                     | -       | $\psi \geq$ (%)          |

|     |         |              |
|-----|---------|--------------|
| Akv | -       | Akv $\geq$ J |
| HBS | 123-321 | -            |
| HRC | 30      | -            |

### 17-7PH Mechanical Properties

|                  |         |                          |
|------------------|---------|--------------------------|
| Tensile strength | 231-231 | $\sigma_b$ /MPa          |
| Yield Strength   | 154     | $\sigma_{0.2} \geq$ /MPa |
| Elongation       | 56      | $\delta_5 \geq$ (%)      |
| $\psi$           | -       | $\psi \geq$ (%)          |
| Akv              | -       | Akv $\geq$ J             |
| HBS              | 235-268 | -                        |
| HRC              | 30      | -                        |

### 17-7PH Heat Treatment Regime

| Annealing | Quenching | Tempering | Normalizing | Q & T |
|-----------|-----------|-----------|-------------|-------|
| √         | √         | √         | √           | √     |

### 17-7PH Range of products

| Product type    | Products                                 | Dimension                  | Processes                                   | Deliver Status  |
|-----------------|--|----------------------------|---|---|
| Plates / Sheets | Plates / Sheets                          | 0.08-200mm(T)*W*L          | Forging, hot rolling and cold rolling       | Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting |
| Steel Bar       | Round Bar, Flat Bar, Square Bar          | $\Phi$ 8-1200mm*L          | Forging, hot rolling and cold rolling, Cast | Black, Rough Turning, Shot Blasting,                          |
| Coil / Strip    | Steel Coil /Steel Strip                  | 0.03-16.0x1200mm           | Cold-Rolled & Hot-Rolled                    | Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting |
| Pipes / Tubes   | Seamless Pipes/Tubes, Welded Pipes/Tubes | OD:6-219mm x WT:0.5-20.0mm | Hot extrusion, Cold Drawn, Welded           | Annealed, Solution and Aging, Q+T, ACID-WASHED                |

## We can produce Stainless Steels the specifications follows:

Note:

- (1) listed in the table apex diameter (d), to steel thickness (a) multiples said.
- (2) in the ASTM A6 standard specified scope can meet any additional conditions.
- (3) from the standard for 50 mm (2 in).

Mechanical properties

Mechanische Eigenschaften

Caracteristiques mecaniques

ReH Minimum yield strength / Mindestwert der oberen Streckgrenze / Limite d'élasticité minimale

Rm Tensile strength / Zugfestigkeit / Resistance a la traction

A Minimum elongation / Mindestwert der Bruchdehnung / Allongement minimal

J Notch impact test / Kerbschlagbiegeversuch / Essai de flexion par choc

Round bar:

Diameter : 1mm-2000mm

Square bar:

Size: 50mm \* 50mm-600mm \*600mm

Plate steel/flat bar:

Size: Thickness: 0.1mm-800mm Width: 10mm to 1500mm

Tube/pipe:

Size: OD: 6-219mm WT: 1-35 mm.

Cold-rolled sheet: Thickness: 2-5mm Width:1000mm Length: 2000mm

Hot-rolled sheet: Thickness:6-80mm Width: 210-610mm

Length: We can supply any length based on the customer's requirement.

Forging/hot rolling/ extrusion of steel.

Forging: Shafts with flanks/pipes/tubes/slugs/donuts/cubes/other shapes

Finished goods condition: hot forging/hot rolling + annealing/normalizing + tempering/quenching + tempering/any conditions based on the customer's requirement

Surface conditions: scaled (hot working finish)/ground/rough machining/fine machining/based on the customer's requirement

Furnaces for metallurgical processing: electrode arc + LF/VD/VOD/ESR/Vacuum consumable electrode.

Ultrasonic inspection: 100% ultrasonic inspection for any imperfections or based on the customer's requirement.

UTS according to SEP 1921 C/c,D/d,E/e;A388 or GB/T 6402

Excellent service for all kinds of industries, with advantages of technologies, equipment and price.

We serve you with our honesty, integrity, and professionalism.